



REF : RPMTFC 2025/02

Resin Paint MTFC

DESCRIPTION

Resin Paint MTFC is a two-pack solvent-free high-build epoxy resin primer / coating developed to provide protective properties to concrete substrates. Resin Paint MTFC is specially formulated to have increased tolerance to residual moisture in the substrate. Resin Paint MTFC is chemical and abrasion resistant. easily applied by roller and brush.

ADVANTAGES

- High-build finish
- Solvent free
- Hygienic and easily cleaned
- Moisture tolerant
- Excellent slip resistance with the inclusion of selected aggregates
- Excellent high gloss finish
- Available in a wide range of colours

RECOMMENDED USES

- Food processing and beverage areas
- Chemical plant rooms
- Engineering workshops
- Automotive & aviation areas
- Factory units
- Warehouses
- Excellent for all demarcation and walkways

PRODUCT INFORMATION

System thickness (dry)	Solids content by weight	Pack sizes	Pack make up	Shelf life	Storage
250-300 microns (per coat)	100 %	5 kg. & 10 kg.	1 X Base 1 X Hardener	12 Months (Base & Hardener)	Keep out of direct sunlight. Store in a dry place, not below 15°C

DRYING TIMES & COVERAGE RATES at 20°C

Coverage rate	Pot life	Recoat time	Light traffic	Full traffic	Full chemical cure
5 Kg. will cover 20 m ² @ 200 microns thickness	15 Minutes from mixing	8 hours or once surface has lost tackiness	8 Hours	18 Hours	Up to 7 Days

Specification

Product : Resin Paint MTFC

Finish : Gloss Finish

Thickness : 200-300 microns

Colour : See Resin Paint Colour Chart

Products required for this system

Prime : Resin Paint Primer DPM where required

System : two coats Resin Paint MTFC at required thickness

Surface Seal : Not required

Preparation

New Concrete Floors: New concrete must be clean, sound, dry and fully cured and surface laitance removed preferably by enclosed shot blasting or mechanical grinding, a minimum strength of 25N/mm² is required.

Existing Concrete Floors: Remove all dirt, oil, grease or other surface contaminants by enclosed shot blasting, scarification or mechanical grinding. Fats, oils or greases must be removed by mechanical means and detergent washing. Local repairs should be carried out using **Resin Paint Concrete Repair**

Priming

Open, porous substrates may require priming with **Resin Paint Primer DPM**.

If the substrate appears very weak and dusts easily the matrix of the screed can be strengthened by installing **Resin Paint Binder** a low viscosity binder formulated for defective substrates. (Contact Resin Paint for further information).

Application

The ambient temperatures of the areas should not be allowed to fall below 10°C throughout the application and the curing period, as this could have an adverse effect on the appearance and colour of the system. Surface temperature must be above 5°C.

Where possible it is recommended that the application area is heated to a minimum temperature of 15°C ideally to allow the ambient and substrate temperature to stabilise prior to installation.

Mixing: Pre-mix the coloured base component to a uniform consistency then mix the entire contents of the base with the hardener. If a separate mixing bucket is being used mix thoroughly ensuring all contents of both components are removed from the buckets supplied. Mix using a slow speed electric mixer for approximately two minutes or until the two components have fully combined.

The mixed unit should be applied immediately by roller or brush with a consistent procedure. Floor areas should be cross-rolled to ensure even application and to minimise roller marks.

Coverage rates will depend on profile and porosity of the substrate.

Category Guide

FeRFA Category : 3

Technical Information

The following figures are obtained from laboratory tests and our experience with this product .

Slip Resistance	Dry	> 50
	Wet	Please consult Resin Paint
Method BS7976 pt1-3 2002		
Abrasion Resistance		n/a
Method BS8204 /ASTM D4060		
Temperature Resistance		Tolerant of temperatures up to 45°C
Chemical Resistance		Good Chemical Resistance Consult Resin Paint on specific materials
Compressive Strength		n/a
Flexural Strength		n/a
Tensile Strength		n/a
VOC		197 g/l Calculation based on a full mixed unit
Life Expectancy		3-5 years plus Subjected to Industrial Fork Lift Traffic Resin Paint terms and conditions will apply

Maintenance and Cleaning

Resin Paint recommend that **Resin Paint MTFC** should be cleaned with a regular industrial cleaning regime with a floor scrubber utilising **Industrial Floor Cleaner** or similar with dirty water being removed.

All surfaces should be thoroughly rinsed with clean water after the use of chemical cleaners.

Health and Safety

Resin Paint MTFC is formulated from materials designed to achieve the highest level of performance as safely as possible. However, specific components require proper handling and suitable equipment, this information is given in the relevant safety data sheets. In all cases, spillages or skin contamination should be cleaned as soon as practically possible, by dry wiping of the affected area, and thorough washing with soap and water.

The information given in this data sheet is derived from tests and experience with the products and is believed to be reliable. The information is offered without guarantee to enable purchasers to determine for themselves the suitability of the product for their particular application. Any specification or advice given by the Resin Paint Limited or its agents is based on the information supplied by the purchaser. Resin Paint cannot be held accountable for errors or omissions as a result of that information being incorrect or incomplete. No undertakings can be given against infringement of patents. Some materials are derived from natural sources. As such some variation may occur. Site conditions may also contribute to variation in finish and colour.